HORIZONTAL VESSEL - GENERAL INSPECTION FORM									
District: Grande P	rairie, A.B.	Skid No.							
Facility: South Spirit River Battery Unit # 1				Location (LSD): 09-09-77-07 W6M					
Vessel Name & Equipment Number: Flare Knock Out Drum									
Orientation: Horizontal									
Status: In Ser	vice		Regulatory Inspection						
Status: In St.	1100	PRESSURE VE	NAMEPLATE DATA						
"A" or "G" or "S" (Sask.) or BC Regi		CRN Number						
·	162556		P 6520.2						
A Vessel serial numbe	462576 11706		Sizo: 49 in v 12 ft						
Shell thickness: 9.5			Size: 48 in x 12 ft						
				Shell material: SA-516-70N					
Head thickness: 7.9				Head material: SA-516-70N					
Tube wall thickness				Tube material:					
Tube diameter:			Tube length:						
Channel thickness:				Channel material:					
MAWP	Shell: 50 PSI			Operating pressure	Shell:				
	Tubes:			Tubes:					
Design Temp.	Shell: 300 Deg	g. F		Operating temperature	Shell:				
	Tubes:				Tubes:				
X-ray: RT-1				Heat treatment: Nil					
Code parameters: A	SME VIII Div.1			Joint efficiency (if on nameplate):					
Manufacturer: E ar		ocess Equipment	Year built: 2001						
Corrosion allowance				Manway: Yes					
		PRESSURE SAFET	Y VAI	VE NAMEPLATE DATA	1	_			
Tag Number(s)			1	ufacturer /Model / Serial# Code Stamp	Capacity (Scfm)	Size	Set Date		
Shell Side No PSV on this system									
	SE	RVICE CONDTIO	NS-INI	DICATE ALL THAT APP	LY				
Sweet X Sour Oil			X	Gas X		Water X			
Amine LPG Con			Con	densate X	Air		Glycol		
Other (Describe):									
Inspection Interval									
Mechanical Integrity CoordinatorDate									

Fill out all forms as completely as possible. All information is important! Use back of sheets to record additional information or sketch if required.

Canadian Natural Resources Limited			l		~	
External Inspection Items	G	F	P	N/A	Comments	
Insulation Verify sealed around manways,						
nozzles, no damage present, and there is no	X				Vessel is fully insulated – no open or torn sections.	
egress of moisture. Are straps secured?						
External Condition Assess paint condition,						
areas peeling, record any corrosion, damage,	X				Paint in good condition – no exposed metal, no external	
distortion etc (record location, size and depth					corrosion observed.	
of corrosion or damage)						
Leakage Record any leakage at flanges,	X				No leaks observed.	
threaded joints, weep holes on repads, etc.						
Skirt: Assess condition of paint, fire	X				Saddle:	
protection, and concrete. Look for corrosion,					No deflection or distortion - no signs of leaks.	
buckling, dents, etc. Look at vessel surface						
area near supports. Verify no signs of leakage						
at attachment to vessel and attachment welds					Ground wire firmly attached to saddle.	
are acceptable. Is ground wire attached?						
Anchor Bolts Hammer tap to ensure secure.						
Look for corrosion, cracking in threads or	X				Firmly bolted to skid.	
signs of deformation.						
Concrete foundation Check for cracks,				X		
spalling, etc.						
Ladder / Platform Describe general		X			No ladder	
condition, ensure support is secure to vessel,						
and describe any hazards.						
Nozzle Assess paint, look for leakage, and					Stud threads are fully engaged to nuts – no short bolts.	
ensure stud threads are fully engaged. Record	X				No damage or deflections observed – no leaks.	
any damage, deflection, etc. Are nozzles					Insulation covers all - nozzles are not gusseted.	
gusseted? Inspect gussets for cracking.						
Gauges Ensure gauges are visible, working,				X	No gauges visible.	
no leakage, and suitable for range of MAWP/						
Temp.						
External Piping Ensure pipe is well					Inlet and Outlet piping is well supported, all clamps,	
supported. All clamps, supports, shoes, etc. in	X				supports, and shoes are in place.	
place. Look for evidence of structural					No structural overloads or deflections noted.	
overload, deflection, etc. Paint condition,					Piping is insulated – no open or torn areas.	
external corrosion?						
Valving Ensure no leaks are visible. Valves					Truck pump out valve is properly supported.	
are properly supported and chained if	X					
necessary.						
PSV Ensure PSV is set at pressure at or below				X	No PSV on this system – vents to atmosphere.	
that of vessel. Discharge piping is same size as						
valve outlet and is properly supported and						
routed. Are psv seals in place? Ensure no						
block valves between psv and vessel, or if						
there is that they are locked/sealed open.						
NDE methods Was UT/ MPI done on vessel	X				Ultrasonic thickness survey carried out- no metal thickness	
(MI coordinator to review results)					detected below nominal minus corrosion allowance.	
Other Observations:						

Inspected By: Dellas Wiedman Date: June 19, 2007

Internal Inspection Items	G	F	P	N/A	Comments
Coating Assess coating. Describe area coated,	X				100 % internally coated – 1 small area of coating missing at
general condition of coating.					6:00 position o internal edge of man way nozzle – no
					corrosion.
Anodes. How many, type, condition. %				X	No anodes
consumed. Are they being replaced?					
J & 1					
Internal Piping Is there any? If so, carbon or	X				Heat Medium coil x 2: Good condition – no scale, no
stainless steel. Describe condition, dents,					corrosion.
corrosion, erosion, etc. Ensure supports are					
secure and any bolts are suitable for future					
use.					
Trays How many? Type of material. Are				X	No trays.
valves in place. Check for erosion/corrosion;					
wear on tray valve legs. Cleanliness?					
Baffles, deflector plates, etc. If present,	X				Inlet deflector x 2 - in place – no broken members – no
describe condition. Look closely at welds					exposed metal.
attached to vessel wall.					Float intact.
					Vortex breaker attached.
East Head Note all corrosion, erosion or	X				Fully coated – no exposed metal.
mechanical damage. (If vessel is horizontal					- and compared management
identify direction of this head)					
West Head Note all corrosion, erosion or	X				Fully coated – no exposed metal.
mechanical damage. (If vessel is horizontal					- and compared management
identify direction of this head)					
Shell Sections Record number of shell		X			1 can section – fully coated – no exposed metal to shell
sections. Record location, size and depth of all					sections. 1 small exposed area on man way access to shell
erosion, corrosion or mechanical damage.					area – no corrosion.
Describe general condition. If any corrosion					
greater than corrosion allowance is observed					
in either shell or head, discuss with Chief					
Inspector before closing vessel.					
Demister pad Is it in place? Is it clean? If any				X	No demister in this vessel.
corrosion is apparent in vessel, lift pad and					
check top head for corrosion.					
Welds Inspect all welds, including attachment	X				Good condition, viewed through coating - no previous
welds. Record all service-related damages and					corrosion or pitting.
if there is any discuss with Chief Inspector					
before closing.					
Repairs Required. If yes, ensure procedure		X			1. Hand patch coating on man way access.
and copy of AB 40 is on file, and one sent to					, v
local ABSA, and Chief Inspector					
· • • • • • • • • • • • • • • • • • • •					
NDE Was any NDE done. (MI coordinator to	X				No internal NDE carried out at this time – internal is
review results)					coated with epoxy.
'					

Recommendations or corrective actions: Vessel is Fit for Service or describe corrective actions required) (MIC to review corrective actions with Operations, discuss with Chief Inspector where necessary, and get remedial action implemented)


Other Observations:

Recommendations: 1. Hand patch coating at man way access.

Summary: This vessel is in good overall condition, visual internal and external carried out -1 small area of coating failure - no corrosion or pitting detected.

Vessel is fit for service

Inspected By: Dellas Wiedman **Date:** June 19 – 2007






Vessel Overview





Man way access



Specific gravity float, heat medium coil and vortex breaker. Heat coil in opposite head





Inlet Diffusers



View from internal surface of coating failure